

ceraclac original pro

Description			
Floor covering element with mineral coreboard for glueless installation			
Fields of use			
ceraclac original pro is suitable for heavy domestic use and heavy commercial use (class 23/33 EN 685) "Allgemeine bauaufsichtliche Zulassung": Z-156.610-488			
Technical details		Design	
Dimensions (Decor)	588 x 393 mm		1 Layer X-Protect Surface Surface depends on design - light gloss - matt de luxe - slate decor
Thickness of element	19,6 mm		2 Coreboard HGF (high resistant plaster board)
Package	Carton: 3 elements / 0,68 m ² / 20 kg Pallet: 52 cartons / 35,36 m ² / 1070 kg		3 Backing (laminated sheet)
Quality Guarantee*	Domestic area: 15 years Commercial area: 5 years		4 Edge Sealing Protection against moisture
		5 Clic-system (glueless) Clic-system Loc-Tec Pro	6 Types of joint Variante "style", "structure" or "plain" depends on design
Classification			
		Test Method Standard	Marking acc. Standard
	Level of use 23 Heavy domestic use	EN 685	Corridors, living rooms, kitchens, home offices
	Level of use 33 Heavy commercial use	EN 685	Large offices, public buildings, department stores
	Clic system with spring mechanism	-	patented joint system by Välinge Innovation Optimum fit with longer durability
	Coreboard	-	High load capacity of pressure and point
	Surface	-	Shockproof and strong against hits
	Suitable for machine	WT method	Suitable for Kärcher Floor scrubber BR 400
	Abrasion resistance	EN 13329	AC 5
	Reaction to fire	DIN 4102 T1 EN 13501-1	B1 B _{fl} - s1
	Dynamic coefficient of friction	EN 13893 EN 14041	μ ≥ 0.3 DS
	Resistance to staining	EN 438-2	Materials of group 1 + 2: ≥ grade 5 Materials of group 3: ≥ grade 4
	Resistance to cigarette burns	EN 438-2	Resistant (no damaging of the surface) ≥ Grade 4
	Light fastness	EN 438-2	Grey scale: ≥ 4
	Static indentation	EN 433	No visible change, i.e. ≤ 0,01 mm indentation using a straight steel cylinder, Ø = 11,30 mm (in test)
	Effect of a furniture leg	EN 424	No visible damage, when tested with foot type 0 (in test)
	Effect of a castor chair	EN 425	No change in appearance or damage, as defined in EN 425. Single-wheel castors, as defined in EN 12529:1998, 5.4.4.2 (Type W) shall be used.
	Anti-Static characteristics	DIN EN 1815 EN 14041	ASF 2
	Thermal resistance Underfloor heating - suitable in connection with underlay material and PE-foil as moisture barrier	DIN EN 12667	≤ 0,15 m ² k/w - floating installation (in test)
	Formaldehyde emission	EN 717-2	E 1
Environment/Disposal		<u>Private disposal:</u> like laminated furniture; possible with normal domestic refuse <u>Commercial disposal:</u>	Refuse-key-no. AVV 170802

Relevant information:
 - Cleaning and care: see separate cleaning & care instruction.
 - ceraclac can also be installed completely glued to the subfloor. Please check details with our technical department.
 - Technical subjects can be changed by Witex.

*) acc. to Witex quality guarantee description