

marena maxi V2

| Description | | | | | | | | | | | | | |
|---|--|---|---|---|--|---|---------------------------------------|---|-----------------------------------|---|--|---|--|
| Direct Pressure Laminate according to EN 13329 for glueless installation | | | | | | | | | | | | | |
| Fields of use | | | | | | | | | | | | | |
| Laminate marena maxi V2 is suitable for heavy domestic and general commercial use (EN 13329 - 32) "Allgemeine bauaufsichtliche Zulassung": Z-156.606-410 | | | | | | | | | | | | | |
| Technical details | Design | | | | | | | | | | | | |
| Dimensions (Decor) | 1376 x 240 mm | | | | | | | | | | | | |
| Thickness of element | 8 mm | | | | | | | | | | | | |
| Package | Pack: 7 elements / 2,31 m ² / 17,55 kg Pallet: 51 packs / 117,81 m ² / 910 kg | | | | | | | | | | | | |
| Quality Guarantee* | 25 years / lifetime 5 years | | | | | | | | | | | | |
| | | | | | | | | | | | | | |
| | | | | | | | | | | | | | |
| <table border="1"> <tr> <td>1</td> <td>Overlay Especially resistant melamine resin overlay</td> </tr> <tr> <td colspan="2">Surface (depend on décor) - hand-scraped I - rough sawn - silk matt - synchronous pore with two-sided joint (V2)</td> </tr> <tr> <td>2</td> <td>Decor paper Decorative film</td> </tr> <tr> <td>3</td> <td>Coreboard Aqua-Protect®</td> </tr> <tr> <td>4</td> <td>Edge Sealing Protection against moisture</td> </tr> <tr> <td>5</td> <td>Click system (glueless) LocTec click joint</td> </tr> </table> | | 1 | Overlay Especially resistant melamine resin overlay | Surface (depend on décor) - hand-scraped I - rough sawn - silk matt - synchronous pore with two-sided joint (V2) | | 2 | Decor paper Decorative film | 3 | Coreboard Aqua-Protect® | 4 | Edge Sealing Protection against moisture | 5 | Click system (glueless) LocTec click joint |
| 1 | Overlay Especially resistant melamine resin overlay | | | | | | | | | | | | |
| Surface (depend on décor) - hand-scraped I - rough sawn - silk matt - synchronous pore with two-sided joint (V2) | | | | | | | | | | | | | |
| 2 | Decor paper Decorative film | | | | | | | | | | | | |
| 3 | Coreboard Aqua-Protect® | | | | | | | | | | | | |
| 4 | Edge Sealing Protection against moisture | | | | | | | | | | | | |
| 5 | Click system (glueless) LocTec click joint | | | | | | | | | | | | |
| Classification | | | | | | | | | | | | | |
| | Test Method Standard | Marking acc. Standard | | | | | | | | | | | |
| Level of use 23 Heavy domestic use | EN 13329 | Corridors, living rooms, kitchens, home offices | | | | | | | | | | | |
| Level of use 32 General commercial use | EN 13329 | Offices, boutiques, cafés | | | | | | | | | | | |
| Loc Tec | - | Optimum fit with longer durability | | | | | | | | | | | |
| Aqua Protect | - | Coreboard protected against moisture | | | | | | | | | | | |
| Authentic | - | - | | | | | | | | | | | |
| AC4 | EN 13329, annex E | AC 4 | | | | | | | | | | | |
| Impact resistance | EN 13329, annex F | IC 2 | | | | | | | | | | | |
| Reaction to fire | DIN 4102 T1 EN 13501-1 | B1 C _{fl} s1 | | | | | | | | | | | |
| Dynamic coefficient of friction | EN 13893 EN 14041 | μ ≥ 0.3 DS | | | | | | | | | | | |
| Anti Static | Test of Witex according to DIN EN 1815 | Witex laboratory test is fulfilled | | | | | | | | | | | |
| Resistance to staining | EN 438-2 | Materials of group 1 + 2: ≥ grade 5 Materials of group 3: ≥ grade 4 | | | | | | | | | | | |
| Resistance to cigarette burns | EN 438-2 | Slight change of the surface ≥ grade 4 | | | | | | | | | | | |
| Light fastness | EN ISO 105 - B02 EN 20105 - A02 | Blue wool scale: ≥ 6 Grey scale: ≥ 4 | | | | | | | | | | | |
| Static indentation | EN 433 | No visible change, i.e. ≤ 0,01 mm indentation using a straight steel cylinder, Ø = 11,30 mm. | | | | | | | | | | | |
| Effect of a furniture leg | EN 424 | No visible damage, when tested with foot type 0 | | | | | | | | | | | |
| Effect of a castor chair | EN 425 | No change in appearance or damage, as defined in EN 425. Single-wheel castors, as defined in EN 12529:1998, 5.4.4.2 (Type W) shall be used. | | | | | | | | | | | |
| Thermal resistance Underfloor heating - suitable in connection with underlay material and PE-foil as moisture barrier | DIN EN 12664 | < 0,06 (m ² K)/W - floating installation | | | | | | | | | | | |
| E1 | DIN EN 14041 | E1 | | | | | | | | | | | |
| Environment/Disposal | <u>Private disposal:</u> like laminated furniture; possible with normal domestic refuse <u>Commercial disposal:</u> | Refuse-key-no. AVV 170201 | | | | | | | | | | | |

* acc. to the Witex guarantee provisions
** acc. to the Witex implementation provisions

Relevant Information:
- Cleaning and care: see separate cleaning & care instruction
- No release for glue-down
- Technical subjects can be changed by Witex